

SGS

Test Report

No. 2019532/JL

Date : Nov 15 2005

Page 1 of 1

GOODAY INT'L LTD.
21/F, BEL TRADE COMM. BLDG.,
NO.1-3 BURROUS ST.
WANCHAI, HONG KONG

Report on the submitted plastic sample said to be POLYCARBONATE RESIN GRADE: L-1250Y.

SGS Job No. : 1911577
Manufacturer : TEIJIN POLYCARBONATE CHINA LTD
Country of Origin : CHINA
Sample Receiving Date : NOV 10 2005
Testing Period : NOV 11-14 2005

Test Requested : For compliance with the Food and Drug Administration Regulations for determining the amount of extractives from polycarbonate polymers.

Test Method : With reference to US FDA 21 CFR 177.1580.

Test Results	Extractants and Conditions	Results, (%)	Limit (%)
	Distilled Water at reflux temperature for 6 hours	0.03	0.15
	50% Ethanol at reflux temperature for 6 hours	0.02	0.15
	n-Heptane at reflux temperature for 6 hours	< 0.02	0.15

Note : < = less than


Sample Description :

1. Transparent Plastic (Pellet)

Conclusion : When tested as specified, the submitted plastic sample complies with the Specifications for polycarbonate polymers requirement stated in US FDA 21 CFR 177.1580.

*** End of Report ***

Signed for and on behalf of
SGS Hong Kong Ltd.


Froelito Y. Aguila
Senior Laboratory Executive

This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf. Attention is drawn to the limitations of liability, indemnification and jurisdictional issues defined therein. The results shown in this test report refer only to the sample(s) tested unless otherwise stated. This Test Report cannot be reproduced, except in full, without prior written permission of the Company.

H12375773

SGS Hong Kong Ltd. | 5/F - 8/F & 28/F - 29/F, Metropole Square, 2 On Yiu Street, Siu Lek Yuen, Sham Shui Po, Hong Kong. t (852) 2334 4481 f (852) 2784 3128 www.hk.sgs.com